

## Sutper®TPE E2010001

## **Product Description**

A soft, colorable SEBS-based thermoplastic elastomer (TPE) compound. The product has uniform particle size and is free of impurities, offering excellent physical properties and chemical resistance.

<b>Specifications</b>	
Applications	•Injection molding Car floor mat
Environmental	•RoHS compliant
Appearance	•Black
Form	•Granules
Molding method	•Injection molding
Availability	•Europe
	•North America
	•Asia
	•Africa & Middle East

Physical Properties	<b>Typical Value</b>	Unit	<b>Test Method</b>
Density	0.98	g/cm <sup>3</sup>	ASTM D792
Melt Flow Index (190°C*2.16kg)	50	g/10min	ASTM D1238

Hardness	Typical Value	Unit	<b>Test Method</b>	
Shore A,3sec,23°C	82	A	ASTM D2240	
<b>Mechanical Properties</b>	<b>Typical Value</b>	Unit	<b>Test Method</b>	
100% Tensile Strength - Vertical Flow (23°C)	3.0	Mpa	ASTM D412	
Tensile Strength - Vertical Flow (23°C)	8.0	Mpa	ASTM D412	
Break Elongation-Vertical Flow23°C	600	%	ASTM D412	
Tear Strength -Vertical Flow 23°C Die C	40	KN/m	ASTM D624	

## **Additional Information**

- 1. The above test data were obtained using fan gate injection molded specimens with dimensions of  $110 \text{ mm} \times 80 \text{ mm} \times 2 \text{ mm}$ . The tensile strength, elongation at break, and stress at a given elongation were tested perpendicular to the flow direction, while tear strength was tested along the flow direction.
- 2. The properties listed are typical and should not be considered technical specifications or part of an agreement.
- 3. The user should be aware that Sutper needs to confirm all final details before taking any action based on the information and recommendations in this document.

Tel (Whatsapp): +8615980053877