

Sutper®TPE E4010018

Product Description

A soft, colorable SEBS-based thermoplastic elastomer (TPE) compound. The product has uniform particle size and is free of impurities, offering excellent physical properties and chemical resistance.

| Specifications | |
|----------------|---|
| Applications | •Single-component injection molding handle material |
| Environmental | •RoHS compliant |
| Appearance | •White |
| Form | •Granules |
| Molding method | •Injection molding |
| Availability | •Europe |
| | •North America |
| | •Asia |
| | •Africa & Middle East |

| Physical Properties | Typical Value | Unit | Test Method |
|--------------------------------|----------------------|-------------------|-------------|
| Density | 1.1 | g/cm ³ | ASTM D792 |
| Melt Flow Index (190°C*2.16kg) | 40 | g/10min | ASTM D1238 |

| Hardness | Typical Value | Unit | Test Method |
|--|----------------------|------|--------------------|
| Shore A,1sec,23°C | 60 | А | ASTM D2240 |
| | | | |
| Mechanical Properties | Typical Value | Unit | Test Method |
| 100% Tensile Strength - Vertical Flow (23°C) | 1.0 | Mpa | ASTM D412 |
| Tensile Strength - Vertical Flow (23°C) | 2.0 | Mpa | ASTM D412 |
| Break Elongation-Vertical Flow23°C | 500 | % | ASTM D412 |
| Tear Strength -Vertical Flow 23°C Die C | 10 | KN/m | ASTM D624 |

Additional Information

- 1. The above test data were obtained using fan gate injection molded specimens with dimensions of 110 mm \times 80 mm \times 2 mm. The tensile strength, elongation at break, and stress at a given elongation were tested perpendicular to the flow direction, while tear strength was tested along the flow direction.
- 2. The properties listed are typical and should not be considered technical specifications or part of an agreement.
- 3. The user should be aware that Sutper needs to confirm all final details before taking any action based on the information and recommendations in this document.