

Sutper®TPE E5010002

Product Description

A soft, colorable SEBS-based thermoplastic elastomer (TPE) compound. The product has uniform particle size and is free of impurities, offering excellent physical properties and chemical resistance.

Specifications	
Applications	•Single-component injection molding PP material
Environmental	•RoHS compliant
Appearance	•Translucent
Form	•Granules
Molding method	•Injection molding
Availability	•Europe
	•North America
	•Asia
	•Africa & Middle East

Physical Properties	Typical Value	Unit	Test Method
Density	0.88	g/cm ³	ASTM D792
Melt Flow Index (190°C*2.16kg)	5	g/10min	ASTM D1238

Hardness	Typical Value	Unit	Test Method
Shore A,1sec,23°C	35	A	ASTM D2240
Mechanical Properties	Typical Value	Unit	Test Method
100% Tensile Strength - Vertical Flow (23°C)	0.6	Mpa	ASTM D412
Tensile Strength - Vertical Flow (23°C)	7.0	Mpa	ASTM D412
Break Elongation-Vertical Flow23°C	900	%	ASTM D412
Tear Strength -Vertical Flow 23°C Die C	15	KN/m	ASTM D624

Additional Information

- 1. The above test data were obtained using fan gate injection molded specimens with dimensions of 110 mm × 80 mm × 2 mm. The tensile strength, elongation at break, and stress at a given elongation were tested perpendicular to the flow direction, while tear strength was tested along the flow direction.
- 2. The properties listed are typical and should not be considered technical specifications or part of an agreement.
- 3. The user should be aware that Sutper needs to confirm all final details before taking any action based on the information and recommendations in this document.

Tel (Whatsapp): +8615980053877