

## Sutper®TPE R2010009

## **Product Description**

A soft, colorable SBS-based thermoplastic elastomer (TPE) compound. The product has uniform particle size and is free of impurities, offering excellent physical properties and chemical resistance.

<b>Specifications</b>	
Applications	• single-component injection molding (gangbao)
Environmental	•RoHS compliant
Appearance	•natural color
Form	•Granules
Molding method	•Injection molding
Availability	•Europe
	•North America
	•Asia
	•Africa & Middle East

Physical Properties	Typical Value	Unit	<b>Test Method</b>
Density	0.99	g/cm <sup>3</sup>	ASTM D792
Melt Flow Index (190°C*5kg)	4	g/10min	ASTM D1238

Hardness	Typical Value	Unit	<b>Test Method</b>	
Shore D,1sec,23°C	65	D	ASTM D2240	
<b>Mechanical Properties</b>	Typical Value	Unit	Test Method	
100% Tensile Strength - vertical flow (23°C)	8	Mpa	ASTM D412	
Tensile Strength - Vertical Flow (23°C)	14	Mpa	ASTM D412	
Break Elongation-Vertical Flow23°C	500	%	ASTM D412	
Tear Strength -Vertical Flow 23°C Die C	52	KN/m	ASTM D624	

## **Additional Information**

- 1. The above test data were obtained using fan gate injection molded specimens with dimensions of  $110 \text{ mm} \times 80 \text{ mm} \times 2 \text{ mm}$ . The tensile strength, elongation at break, and stress at a given elongation were tested perpendicular to the flow direction, while tear strength was tested along the flow direction.
- 2. The properties listed are typical and should not be considered technical specifications or part of an agreement.
- 3. The user should be aware that Sutper needs to confirm all final details before taking any action based on the information and recommendations in this document.

Tel (Whatsapp): +8615980053877