

Sutper®TPE R3010001

Product Description

A soft, colorable SBS-based thermoplastic elastomer (TPE) compound. The product has uniform particle size and is free of impurities, offering excellent physical properties and chemical resistance.

| Specifications | |
|----------------|------------------------------|
| Applications | • ultra-transparent material |
| Environmental | •RoHS compliant |
| Appearance | •ultra-transparent |
| Form | •Granules |
| Molding method | •Injection molding |
| Availability | •Europe |
| | •North America |
| | •Asia |
| | •Africa & Middle East |

| Physical Properties | Typical Value | Unit | Test Method |
|-------------------------------|----------------------|-------------------|--------------------|
| Density | 0.92 | g/cm ³ | ASTM D792 |
| Melt Flow Index (190°C*1.2kg) | 66 | g/10min | ASTM D1238 |

| Typical Value | Unit | Test Method | |
|---------------|----------------------------------|--|--|
| 15 | A | ASTM D2240 | |
| Typical Value | Unit | Test Method | |
| 0.3 | Mpa | ASTM D412 | |
| 1.5 | Mpa | ASTM D412 | |
| 500 | % | ASTM D412 | |
| 5 | KN/m | ASTM D624 | |
| | 15 Typical Value 0.3 1.5 500 | 15 A Typical Value 0.3 Mpa 1.5 Mpa 500 % | Typical Value Unit Test Method 0.3 Mpa ASTM D412 1.5 Mpa ASTM D412 500 % ASTM D412 |

Additional Information

- 1. The above test data were obtained using fan gate injection molded specimens with dimensions of 110 mm × 80 mm × 2 mm. The tensile strength, elongation at break, and stress at a given elongation were tested perpendicular to the flow direction, while tear strength was tested along the flow direction.
- 2. The properties listed are typical and should not be considered technical specifications or part of an agreement.
- 3. The user should be aware that Sutper needs to confirm all final details before taking any action based on the information and recommendations in this document.

Tel (Whatsapp): +8615980053877