

Sutper®TPV V1010005

Product Description

This product is a type of thermoplastic elastomer (TPE), specifically a softer, and versatile Thermoplastic Vulcanizates (TPV) material. It offers excellent physical and mechanical properties, along with superior chemical resistance and elasticity, it is a polyolefin elastomer that can be fully recycled and reused during production.

Specifications

Applications	•60A general-purpose injection molding grade
Environmental	•RoHS compliant
Appearance	•White
Form	•Granules
Molding method	•Injection Molding
Availability	•Europe •North America •Asia •Africa & Middle East

Physical Properties	Typical Value	Unit	Test Method
Density	0.97	g/cm ³	ASTM D792
Melt Flow Index (230°C*5kg)	12	g/10min	ASTM D1238

Hardness	Typical Value	Unit	Test Method
Shore A,10sec,23°C	60	A	ASTM D2240

Mechanical Properties	Typical Value	Unit	Test Method
100% Tensile Strength - Vertical Flow (23°C)	1.9	Mpa	ASTM D412
Tensile Strength - Vertical Flow (23°C)	5.3	Mpa	ASTM D412
Break Elongation-Vertical Flow23°C	570	%	ASTM D412
Tear Strength -Vertical Flow 23°C Die C	24	KN/m	ASTM D624

Additional Information

- TPV is incompatible with materials such as PVC, so equipment must be cleaned.
- The above test data were obtained using fan gate injection molded specimens with dimensions of 110 mm × 80 mm × 2 mm. The tensile strength, elongation at break, and stress at a given elongation were tested perpendicular to the flow direction, while tear strength was tested along the flow direction.
- The compression rate for compression set is 25%.
- The properties listed are typical and should not be considered technical specifications or part of an agreement.
- The user should be aware that Sutper needs to confirm all final details before taking any action based on the information and recommendations in this document.

Site: <https://www.sutper.com>