

Sutper®TPV V2010002

Product Description

This product is a type of thermoplastic elastomer (TPE), specifically a softer, and versatile Thermoplastic Vulcanizates (TPV) material. It offers excellent physical and mechanical properties, along with superior chemical resistance and elasticity, it is a polyolefin elastomer that can be fully recycled and reused during production.

| Specifications | |
|----------------|---|
| Applications | •Matte temperature and folding resistant dust cover |
| Environmental | •RoHS compliant |
| Appearance | •Black |
| Form | •Granules |
| Molding method | •Blow Molding |
| Availability | •Europe |
| | •North America |
| | •Asia |
| | •Africa & Middle East |

| Physical Properties | Typical Value | Unit | Test Method |
|--|----------------------|-------------------|--------------------|
| Density | 0.97 | g/cm ³ | ASTM D792 |
| Melt Flow Index (230°C*5kg) | 11 | g/10min | ASTM D1238 |
| | | | |
| Hardness | Typical Value | Unit | Test Method |
| Shore A,5sec,23°C | 44 | A | ASTM D2240 |
| | | | |
| Mechanical Properties | Typical Value | Unit | Test Method |
| 100% Tensile Strength - Vertical Flow (23°C) | 9 | Mpa | ASTM D412 |
| Tensile Strength - Vertical Flow (23°C) | 18 | Mpa | ASTM D412 |
| Break Elongation-Vertical Flow23°C | 650 | % | ASTM D412 |
| Tear Strength -Vertical Flow 23°C Die C | 78 | KN/m | ASTM D624 |

Additional Information

- 1. TPV is incompatible with materials such as PVC, so equipment must be cleaned.
- 2. The above test data were obtained using fan gate injection molded specimens with dimensions of $110 \text{ mm} \times 80 \text{ mm} \times 2 \text{ mm}$. The tensile strength, elongation at break, and stress at a given elongation were tested perpendicular to the flow direction, while tear strength was tested along the flow direction.
- 3. The compression rate for compression set is 25%.
- 4. The properties listed are typical and should not be considered technical specifications or part of an agreement.
- 5. The user should be aware that Sutper needs to confirm all final details before taking any action based on the information and recommendations in this document.